

Property	Test Method	Unit	Guarantee Values
Appearance	Visual	- - -	Clear Light Yellow flakes
Epoxide Equivalent	ASTM D1652	g/eq	434-555
Epoxy Value	ASTM D1652	mol/100 g	0.180-0.230
Color(40% in Dioxane)	ASTM 1209	Pt-Co (APHA)	Max 100
Softening Point	DIN 52011	°C	63-75
Hydrolysable Chlorine	ASTM 1726	%wt	Max 0.1

Basparmarket.com