

Property	Test Method	Unit	Guarantee Values
Appearance	Visual	- - -	Clear Light Yellow Liquid
Epoxy Equivalent	ASTM D1652	g/eq	185 - 192
Epoxy Value	ASTM D1652	mol/100g	0.52 - 0.54
Color	ASTM 1209	Pt-Co (APHA)	Max. 50
Viscosity	DIN 53015 @25°C	mpas	10,000-14,000
Hydrolysable Chlorine	ASTM 1726	% wt	Max. 0.1
%Non-Volatile	DIN EN ISO 3251	% wt	Min 99.3

Basparmarket.com