

AKQUICK T100

Description : Dimethylaniline

Specifications;

Density (@20°C) : $0,96 \pm 0,005 \text{ gr/cm}^3$
Appearance : Yellowish, Transparent, Foggy
Freezing Point : $\geq 2,00 \text{ °C}$
N-Metil Aniline Content : $\leq 0,5 \%$
N,N Dimethyl Aniline Content : $\geq 99,0 \%$
Aniline Content : $\leq 0,03 \%$
Water Content : $\leq 0,1 \%$
CAS Nr. : 121-69-7
EINECS/ELINCS Nr : 204-493-5
UN Nr. : 2253

Application : AKQUICK T100 is used as accelerator with SMC, BMC and DMC type resins at room temperature or elevated temperatures.

Usage & Amount : It is recommended to use 1% - 2% in general

Packaging : 25 kgs PE Pail

Handling & Storage : Must be kept between +5 °C and +30 °C. Keep pails tightly closed. Store and handle in a dry, well-ventilated place, away from sources of heat, ignition and direct sunlight in original packaging. Provide grounding and venting in order to prevent static electricity build-up. Avoid any contact with Organic Peroxides.

Shelf Life : 1 Year
For unopened packages at recommended storage conditions.