

EFOX
TERT-BUTYL PEROXYBENZOATE
AKPA PRODUCT DATA SHEET

Product Code EFOX30
Description Tert-Butyl Peroxybenzoate

Specifications;

Density (@20°C) : 0,810 gr/cm³
Appearance : Colorless, Liquid
Viscosity (@20°C) : 6,55 mPa.s
Active Oxygen Content : 8,08%
Peroxide Content : min. 98%
SADT : 60°C
CAS Nr : 614-45-9
UN Nr : 3103

Applications Used as initiator in co-polymerization of Ethylene, Styrene, Acrylonitrile, Vinyl Acetate, Acrylate and Metacrylates. Used during styrene co-polymerization at temperatures between 100 – 140 °C.

Packaging 25 kg PE Pail

Handling & Storage Must be kept between +8 C and +25 C. Keep pails tightly closed. Store and handle in a dry, well-ventilated place, away from sources of heat, ignition and direct sunlight in original packaging. Provide grounding and venting in order to prevent static electricity build-up. Avoid any contact with Amine and Cobalt Accelerators, acids, alkalis and heavy metal compounds such as driers and metal soaps.

Shelf Life 3 Months
For unopened packages at recommended storage conditions