



Anatase Titanium Dioxide A1

Applications

Rubber, paint, plastic, paper making
and printing ink etc

Production Description

Excellent whiteness pigment
Good whiteness, high tinting strength and
strong hiding power

Technical Data

Item	Specification
Purity TiO_2 % $\geq$	98
Matter volatile at 105°C % $\leq$	0.5
Hydrotrope % $\leq$	0.5
Residue on sieve 45 μm % $\leq$	0.1
Color compare with standard	Not lower than
Tinting strength compare with standard % $\geq$	100
PH of suspension, aqueous solution retained	6.5-8.0
Oil absorption g/100g $\leq$	26
Resistivity of aqueous extract Ωm	20
Whiteness % $\geq$	95.0

